







Demonstrated Results

After 15,000 rounds (ambient):

	Baseline Phosphate	Solid Lubricant Coating
Bolt carrier	 ~75% worn	 <5% worn
	 ~90% worn	 <5% worn
Bolt	 ~90% worn on body, ~50% on lugs	 <5% worn on body, ~10% on lugs

FIRED WITH CLP

FIRED DRY

% worn = % totally exposed substrate

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

UNCLASSIFIED

TECHNOLOGY DRIVEN. WARFIGHTER FOCUSED.